



VERIFICATION OF TRANSLATION

RECEIVED
JUL - 1 2003
TECHNOLOGY CENTER 1700

I, Fumio Akiyama, being a citizen of Japan, residing at c/o ASAHINA & CO., NS Bldg., No. 2-22, Tanimachi 2-chome, Chuo-ku, Osaka-shi, Osaka, 540-0012, Japan, do solemnly and sincerely declare as follows:


I am a translator, of ASAHINA & CO., of NS Bldg., No. 2-22, Tanimachi 2-chome, Chuo-ku, Osaka, 540-0012, Japan.

I am well acquainted with the English and Japanese languages.

The attached translation is a true and correct translation into the English language of a certified copy of Japanese Patent Application No. 2000-296436 filed on September 28, 2000.

I declare further that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

This 17th day of June, 2002

by 
Fumio Akiyama

PATENT OFFICE
JAPANESE GOVERNMENT

This is to certify that the annexed is a true copy of the following application as filed with this Office.

Date of Application: September 28, 2000

Application Number: 2000-296436

Applicant(s): KANEKA CORPORATION

August 3, 2001

Commissioner, Patent Office

Kozo Oikawa

Appln. Certification No. Pat. 2001-3067811

[Document Name]	PETITION FOR PATENT APPLICATION
[Reference Number]	OSK-4322
[Lodging Date]	September 28, 2000
[To Whom]	Commissioner of Patent Office
[International Patent Classification]	A61M 1/36
[Inventor]	
[Residence or Address]	1-3-29-101, Nishikoya, Amagasaki-shi, Hyogo-ken
[Name]	Fumiyasu Hirai
[Inventor]	
[Residence or Address]	5-5-35-209, Torikainishi, Settsu-shi, Osaka-fu
[Name]	Tamiji Fujimoto
[Inventor]	
[Residence or Address]	373-901, Takasago-cho Sakaemachi, Takasago-shi, Hyogo-ken
[Name]	Hiroshi Sakurai
[Inventor]	
[Residence or Address]	3-28-33, Higashiochiai, Suma-ku, Kobe-shi, Hyogo-ken
[Name]	Shigeo Furuyoshi
[Patent Applicant]	
[Identification No.]	000000941
[Name]	KANEKA CORPORATION
[Representative]	Masatoshi Takeda
[Indication of Charge]	
[Number in Prepayment File]	005027
[Sum of Payment]	¥21,000

[List of Filing Materials]

[Material Name]	Specification	1
[Material Name]	Drawing	1
[Material Name]	Abstract	1
[Necessity of Proof]	Necessary	

[Document Name]

SPECIFICATION

[Title of the Invention]

ADSORBENT, ADSORBING AND REMOVING PROCESS
AND ADSORBER FOR ENDOGENOUS CANNABINOID

[CLAIMS]

1. An adsorbent for endogenous cannabinoid comprising a water-insoluble material containing a substance whose solubility parameter δ is at most 12 ((cal/cm³)^{1/2}).
2. The adsorbent of Claim 1, wherein said substance is a styrene-divinyl benzene copolymer.
3. The adsorbent of Claim 1, wherein said endogenous cannabinoid is anandamide.
4. The adsorbent of Claim 1, wherein said endogenous cannabinoid is 2-arachidonoylglycerol.
5. A process for adsorbing and removing endogenous cannabinoid comprising a step for contacting the adsorbent of Claim 1 or 2 with fluid containing endogenous cannabinoid.
6. The process of Claim 5, wherein the fluid is body fluid.

7. An adsorber for endogenous cannabinoid comprising a container having a fluid inlet, a fluid outlet and a means for preventing the adsorbent from escaping outside the container, wherein the container is filled with the adsorbent of Claim 1 or 2.

[DETAILED EXPLANATION OF THE INVENTION]

[Technical Field of the Invention]

The present invention relates to an adsorbent for adsorbing and removing endogenous cannabinoid from body fluid, a process for adsorbing and removing endogenous cannabinoid, and an adsorber for endogenous cannabinoid using the same.

[Prior Art]

It is known that cannabinoids, the main substance of the physiological action of marijuana (cannabis), brings about mental effects such as hallucination and feeling of euphoria. As cannabinoid receptors, a receptor (CB1) expressed in central nerves and a receptor (CB2) expressed in peripheral immune cells are known. Endogenous ligands to these cannabinoid receptors, i.e., the ligand generated in living bodies are called endogenous cannabinoid. Known examples of the endogenous cannabinoid are anandamide and 2-arachidonoylglycerol (hereinafter referred to as 2-AG).

The endogenous cannabinoid bears various physiological activities such as (1) drop in blood pressure and bradycardia for cardiovascular system, (2) inhibition of NO generation in macrophages for immune system, (3) defect of memory and inhibition of pain sensation for central nerve system, and (4) induction of endothelial cell apoptosis for coagulation fibrinolysis system.

Recently, it became clear that anandamide is generated in macrophage and 2-AG is generated in blood platelet by means of lipopolysaccharide stimulus (hereinafter referred to as LPS). It is also observed that the generated endogenous cannabinoid causes drop in blood pressure. Furthermore, some raises possibility that the endogenous cannabinoid generated in macrophage or blood platelet is responsible for the blood pressure drop in septic shock. In fact, there is a report that concentrated endogenous cannabinoid was detected in the blood of patients with septic shock.

From these facts, a treatment is expected for the blood pressure drop in septic shock and the like by removing endogenous cannabinoid from body fluid of patients. However, no process for adsorbing and removing endogenous cannabinoid has been available so far. Hence, there has been considerable demand for such process. Yin Wang et al reported that the adsorption of anandamide was possible by means of a substance obtained by fixing an antibiotic, polymyxin B (FEBS Letters, vol. 470, pp151-155, 2000). However, many steps are required in order to prepare such an adsorbent. Besides, the polymyxin B, one of the antibiotics, is very expensive. For these reasons, there is a desire for a process for adsorbing and removing endogenous cannabinoid by using a lower-price substance.

The present invention was carried out in order to solve the above problems.

[Problem to be Solved by the Invention]

The object of the present invention is to provide an adsorbent which can adsorb and remove endogenous cannabinoid in body fluid efficiently, a process for adsorbing and removing endogenous

cannabinoid in body fluid by using the adsorbent, and an adsorber for endogenous cannabinoid.

[Means to Solve the Problem]

The present inventors made an intense studies as to an adsorbent which can adsorb and remove endogenous cannabinoid in body fluid efficiently. As a result, the present invention has been completed based on the findings that an adsorbent comprising a water-insoluble material containing a substance whose solubility parameter δ is at most 12 $((\text{cal}/\text{cm}^3)^{1/2})$ can adsorb and remove endogenous cannabinoid in body fluid efficiently.

That is, the present invention relates to an adsorbent for endogenous cannabinoid comprising a water-insoluble material containing a substance whose solubility parameter δ is at most 12 $((\text{cal}/\text{cm}^3)^{1/2})$.

Said substance is preferably a styrene-divinyl benzene copolymer in a preferred embodiment.

Said endogenous cannabinoid is anandamide in a preferred embodiment.

Said endogenous cannabinoid is 2-AG in a preferred embodiment.

The present invention also relates to a process for adsorbing and removing endogenous cannabinoid comprising a step of contacting the adsorbent of endogenous cannabinoid with fluid containing endogenous cannabinoid.

The fluid is body fluid in a preferred embodiment.

The present invention also relates to an adsorber for endogenous cannabinoid comprising a container having a fluid inlet, a

fluid outlet and a means for preventing the adsorbent from escaping outside the container, wherein the container is filled with the adsorbent of endogenous cannabinoid.

[Embodiment for Carrying out the Invention]

The endogenous cannabinoid in the present invention means endogenous ligands of cannabinoid receptors, i.e., the ligand generated in living bodies. Typical examples of the endogenous cannabinoid are anandamide and 2-AG. Anandamide is represented by the chemical formula $C_{22}H_{37}NO_2$ and has the molecular weight of 347.5. On the other hand, 2-AG is represented by the chemical formula $C_{23}H_{38}O_4$ and has the molecular weight of 378.5.

The body fluid in the present invention means blood, plasma, serum, ascites, lymph, arthral fluid and fragments obtainable therefrom, and other fluid components derived from living organs.

The adsorbent of the present invention comprises a water-insoluble material containing a substance whose solubility parameter δ is at most 12 $((\text{cal}/\text{cm}^3)^{1/2})$, preferably at most 11 $((\text{cal}/\text{cm}^3)^{1/2})$.

A solubility parameter δ of a substance is a value defined by $(\Delta E_v/V)^{1/2}$. Herein, ΔE_v indicates molar evaporation energy of a substance and V indicates molar volume of the substance. $\Delta E_v/V$ indicates evaporation energy per unit volume of the substance and is called cohesive energy density. In case of a polymer, cohesive energy density is determined per repeat unit, but when the molecular structure of the repeat unit is definite, solubility parameter δ can be determined by calculation. The closer solubility parameter δ of a solute to that of a solvent is, the smaller solubility resistance is. Therefore, solubility parameter δ serves as an index for solubility. On the other hand, the

smaller solubility parameter δ is, the less polar and the more hydrophobic the substance is. Solubility parameters of various substances are described on pages 675 to 714, VII, *Polymer Handbook*, 4th ed., edited by J. Brandrup et al. Also, as described in the book, solubility parameter can be determined by experiments when the molecular structure of repeat unit is indefinite as in case of using a commercially available polymer. As a classical approach, there is a process for determining solubility parameters by solvency testing where a target polymer is dissolved in various solvents whose solubility parameters are already known. Also, in case of cross-linked polymers, there is a process for determining solubility parameters from extent of swelling, i.e., a swelling value by immersing a target polymer in various solvents whose solubility parameters are already known. This process is suitable for a styrene-divinyl benzene copolymer and the like. However, the process for determining solubility parameter is not limited thereto.

Examples of the substance whose solubility parameter is at most 12 ((cal/cm³)^{1/2}) are polyethylene, polypropylene, poly(methacrylate ester), poly(acrylate ester), poly(vinyl chloride), polystyrene, a styrene-divinyl benzene copolymer, nylon 6, nylon 66, polytetrafluoroethylene, polysulfone, polyurethane and the like, but not limited thereto.

The water-insoluble material used for the adsorbent of the present invention means a material which is solid at normal temperature under normal pressure and whose solubility to water is extremely small. In the present invention, the water-insoluble material is shaped in particles, plates, fibers, hollow fibers and the like, and the

shape and the size are not particularly limited.

It is preferable that these water-insoluble materials have numerous pores of suitable size, in other words, a porous structure. The material having a porous structure obviously includes the materials having spaces (macropores) formed by agglomeration of minute spheres when one spherical particle is formed from a basic polymer matrix by the agglomeration of minute spheres. However, there are also materials which have pores formed by agglomeration of nuclei in a minute sphere constituting a basic polymer matrix, and those which have pores (micropores) formed when a copolymer having a three-dimensional structure (polymer net) is swelled by an organic solvent having affinity therewith.

Also, water-insoluble materials having a totally porous structure are more preferable than those having a surface porous structure from the viewpoint of adsorption ability per unit volume of the adsorbent. The pore volume and the specific surface area are preferably large to such a degree that the adsorption property is not lost.

It is preferable that the water-insoluble porous material has such a size that the target substance of adsorption may enter at a certain high probability. Since the adsorptive target of the adsorbent of the present invention, i.e., endogenous cannabinoid, has relatively small molecular weight of about 300 to 400, water-insoluble materials having a porous structure is quite adequate for endogenous cannabinoid to enter the pore. Thus, there is no particular limitation for the useful water-insoluble porous material.

In order to improve compatibility with blood, suitable side chain and ligand can be introduced to these materials, or a hydrophilic

material can be coated thereto to such a degree that adsorption ability of endogenous cannabinoid is not lost. Examples of the side chain and the ligand are those which have a hydroxyl group or an amino group. Examples of the hydrophilic material are a polymer of hydroxyethyl methacrylate, cellulose and the like, but not limited thereto.

There are various processes for adsorbing and removing endogenous cannabinoid from body fluid by using the adsorbent of the present invention. As the most convenient process, there is one in which body fluid is taken out, stored in a bag and the like, mixed and contacted with an adsorbent to adsorb and remove endogenous cannabinoid, and then the adsorbent is filtered to obtain body fluid from which endogenous cannabinoid is removed. There is also another process in which an adsorbent is filled into a container having an inlet and an outlet for body fluid as well as a filter which passes body fluid but blocks the adsorbent. In the process, the body fluid is then passed through the container and contacted with the adsorbent. Either method can be used, but the latter process is more suitable for the adsorbent of the present invention. This is because the operation is easier and because endogenous cannabinoid can be removed efficiently on-line from body fluid of patients, especially blood, when the device is incorporated into an extracorporeal circulation circuit.

Though the adsorbent of the present invention is used independently in the herein-mentioned extracorporeal circulation circuit, it can be combined with other extracorporeal circulation treatment systems. For example, combination with dialytic treatment is also possible including an artificial dialysis circuit and the like.

Next, explanation is made as to the adsorber of the present

invention in which the above adsorbent of endogenous cannabinoid is used based on Fig. 1 showing schematic cross-section of one embodiment. In Fig. 1, numeral 1 indicates inlet of fluid, numeral 2 outlet of fluid, numeral 3 the adsorbent of endogenous cannabinoid of the present invention, numerals 4 and 5 a filter which passes fluid and components included in the fluid but blocks the above adsorbent of endogenous cannabinoid, numeral 6 a column and numeral 7 an adsorber of endogenous cannabinoid. However, an adsorber of endogenous cannabinoid is not limited to these examples. Any adsorber may be used as long as it comprises a container which is filled with the above adsorbent and has a fluid inlet, a fluid outlet, and a means for preventing spillage of the adsorbent of endogenous cannabinoid.

Examples of the means for preventing spillage of the adsorbent are filters such as mesh, non-woven fabric and cotton plug. Though there is no particular limitation for shape, material and size of the container, a cylindrical container is preferable regarding the shape. A material having sterilization resistance is preferable for the container. Examples thereof are silicone-coated glass, polypropylene, poly(vinyl chloride), polycarbonate, polysulfone, polymethylpentene and the like. Preferably, the capacity of the container is 50 to 1,500 ml, and the diameter is 2 to 20 cm. More preferably, the capacity of the container is 100 to 800 ml and the diameter is 3 to 15 cm. Most preferably, the capacity of the container is 150 to 400 ml and the diameter is 4 to 10 cm.

Hereinafter the present invention is explained in more detail by means of the following Examples, but the present invention is not limited thereto.

EXAMPLE 1

A water-insoluble material (DIAION HP-20 available from Mitsubishi Chemical Corporation) comprising a styrene-divinyl benzene copolymer which was a substance having solubility parameter δ of about 9 ((cal/cm³)^{1/2}), was taken in an amount of 0.2 ml. Thereto was added 1.2 ml of 50 % ethanol/saline solution in which endogenous cannabinoid, i.e., anandamide (available from Calbiochem-Novabiochem Corporation) was added to adjust the cannabinoid concentration to 0.1 mg/ml. The mixture was shaken at 37°C for two hours. After shaking, supernatant was removed and washed with saline, and then 1.2 ml of 95 % ethanol was added thereto to elute the adsorbed anandamide. By measuring ultraviolet ray absorption of the ethanol-added supernatant at a wavelength of 208 nm, concentration of anandamide was determined, and the amount of adsorption was calculated.

EXAMPLE 2

A water-insoluble material (AMBERLITE XAD-8 available from Organo Corporation) comprising poly(methacrylate ester) which is a substance having solubility parameter δ of about 9 ((cal/cm³)^{1/2}) was used. In the same manner as in Example 1, the material was shaken with anandamide-added 50 % ethanol/saline solution to elute the adsorbed anandamide with ethanol, and the amount of adsorption was calculated.

EXAMPLE 3

A water-insoluble material (a hollow fiber material used for PLASMA SEPARATOR SULFLUX, available from Kaneka Corporation)

comprising polysulfone which is a substance having solubility parameter δ of about 10 ((cal/cm³)^{1/2}) was used. In the same manner as in Example 1, the material was shaken with anandamide-added 50 % ethanol/saline solution to elute the adsorbed anandamide with ethanol, and the amount of adsorption was calculated.

COMPARATIVE EXAMPLE 1

A water-insoluble material (CELLULOFINE GC-200m available from Chisso Corp.) comprising cellulose which is a substance having solubility parameter δ of about 16 ((cal/cm³)^{1/2}) was used. In the same manner as in Example 1, the material was shaken with an anandamide-added 50 % ethanol/saline solution to elute the adsorbed anandamide with ethanol, and the amount of adsorption was calculated.

TABLE 1

	Adsorption amount of anandamide (μ g/ml-adsorbent)	Adsorption ratio (%)
Ex. No. 1	574	95.7
Ex. No. 2	563	93.8
Ex. No. 3	422	70.3
Com. Ex. No. 1	5.5	0.9

EXAMPLE 4

A water-insoluble material (DIAION HP-20 available from Mitsubishi Chemical Corporation) comprising a styrene-divinyl benzene copolymer which is a substance having solubility parameter δ of about 9 ((cal/cm³)^{1/2}), was taken in an amount of 0.2 ml. Thereto was added 1.2

ml of 50 % ethanol/saline solution in which endogenous cannabinoid, i.e., 2-AG (available from Calbiochem-Novabiochem Corporation) was added to adjust the cannabinoid concentration to 0.1 mg/ml. The mixture was shaken at 37°C for two hours. After shaking, supernatant was removed and washed with saline, and then 1.2 ml of 95 % ethanol was added thereto to elute the adsorbed 2-AG. By measuring ultraviolet ray absorption of the ethanol-added supernatant at a wavelength of 208 nm, concentration of 2-AG was determined, and the amount of adsorption was calculated.

EXAMPLE 5

A water-insoluble material (AMBERLITE XAD-8 available from Organo Corporation) comprising poly(methacrylate ester) which is a substance having solubility parameter δ of about 9 ((cal/cm³)^{1/2}) was used. In the same manner as in Example 4, the material was shaken with human 2-AG added 50 % ethanol/saline solution to elute the adsorbed 2-AG with ethanol, and the amount of adsorption was calculated.

EXAMPLE 6

A water-insoluble material (a hollow fiber material used for PLASMA SEPARATOR SULFLUX, available from Kaneka Corporation) comprising polysulfone which is a substance having solubility parameter δ of about 10 ((cal/cm³)^{1/2}) was used. In the same manner as in Example 4, the material was shaken with human 2-AG added 50 % ethanol/saline solution to elute the adsorbed 2-AG with ethanol, and the amount of adsorption was calculated.

COMPARATIVE EXAMPLE 2

A water-insoluble material (CELLULOFINE GC-200m available from Chisso Corp.) comprising cellulose which is a substance having solubility parameter δ of about 16 ((cal/cm³)^{1/2}) was used. In the same manner as in Example 4, the material was shaken with human 2-AG added 50 % ethanol/saline solution to elute the adsorbed 2-AG with ethanol, and the amount of adsorption was calculated.

TABLE 2

	Adsorption amount of 2-AG (μ g/ml-adsorbent)	Adsorption ratio (%)
Ex. No. 4	127	21.2
Ex. No. 5	109	18.2
Ex. No. 6	61.2	10.2
Com. Ex. No. 2	10.4	1.7

[Effect of the Invention]

According to the process of the present invention, by using the adsorbent comprising a water-insoluble material containing a substance whose solubility parameter δ is at most 12 ((cal/cm³)^{1/2}), it is possible to adsorb and remove endogenous cannabinoid in body fluid effectively.

[Brief Description of Drawings]

Fig. 1 is a schematic sectional view showing an embodiment of the adsorber of endogenous cannabinoid according to the present invention.

[Description of Symbols]

1 inlet of fluid

- 2 outlet of fluid
- 3 the adsorbent of endogenous cannabinoid
- 4, 5 a filter which passes fluid and components included in the fluid but blocks the above adsorbent of endogenous cannabinoid
- 6 a column
- 7 an adsorber of endogenous

Information of Applicant's History

Identification Number	[000000941]
1. Date of Revision	August 27, 1990
[Reason for Revision]	New registration
Address	2-4, Nakanoshima 3-chome, Kita-ku, Osaka-shi, Osaka-fu
Name	KANEKA CORPORATION